

Clean Copy of Table 2

Table 2

	n_{sp}/c	T _{mL} (°C)	T _{mH} (°C)	T _{c2} (°C)	Half value width	Whitening		Hardness	Can formability
						280°C	290°C		
Example 1	0.94	221	252	191	0.19	⊙	⊙	3H	⊙
Example 2	0.95	221	254	195	0.18	⊙	⊙	3H	⊙
Comp. Ex. 1	0.79	223	247	179	0.31	×	×	HB	⊙
Example 3	0.84	222	249	184	0.24	⊙	×	2H	⊙
Comp. Ex. 2	0.88	223	252	176	0.39	×	×	H	⊙
Example 4	0.88	231	250	186	0.22	⊙	Δ	2H	⊙
Example 5	0.93	221	253	191	0.19	⊙	⊙	3H	⊙
Comp. Ex. 3	0.75	Not seen	251	166	0.41	×	×	HB	⊙
Comp. Ex. 4	0.79	220	250	179	0.32	Δ	×	H	⊙
Comp. Ex. 5	0.82	218	250	175	0.37	×	×	2H	⊙
Example 7	0.83	220	251	197	0.12	⊙	⊙	3H	⊙
Example 8	0.95	219	252	191	0.19	⊙	⊙	2H	⊙
Example 9	0.82	186	250	184	0.23	⊙	×	H	⊙
Example 10	0.88	254	260	183	0.24	⊙	×	3H	⊙
Example 11	0.95	221	253	194	0.18	⊙	⊙	3H	⊙
Comp. Ex. 6	0.71	Not seen	256	199	0.11	⊙	⊙	3H	×
Comp. Ex. 7	0.95	223	Not seen	167	0.31	×	×	3H	⊙
Example 12	0.81	219	249	181	0.25	⊙	×	H	⊙